



US007141866B1

(12) **United States Patent**
Islam et al.

(10) **Patent No.:** **US 7,141,866 B1**
(45) **Date of Patent:** **Nov. 28, 2006**

(54) **APPARATUS FOR IMPRINTING
LITHOGRAPHY AND FABRICATION
THEREOF**

6,365,059 B1 4/2002 Pechenik
6,407,443 B1 6/2002 Chen et al.
2003/0219992 A1* 11/2003 Schaper 438/748
2004/0156108 A1* 8/2004 Chou et al. 359/566

(75) Inventors: **M. Saif Islam**, Mountain View, CA (US); **Gun Young Jung**, Mountain View, CA (US); **Yong Chen**, Sherman Oaks, CA (US); **R. Stanley Williams**, Redwood City, CA (US)

OTHER PUBLICATIONS

"Making nanowire lattices in a snap", Materialstoday, vol. 6, Issue 5, May 2003, p. 6.
Nicholas A. Melosh, et al., Ultrahigh-Density Nanowire Lattices and Circuits, Scienceexpress, Mar. 13, 2003, pp. 1-4 & 6 figures, www.scienceexpress.org, 10.1126/science.1081940.

(73) Assignee: **Hewlett-Packard Development Company, L.P.**, Houston, TX (US)

* cited by examiner

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

Primary Examiner—Thanhha Pham

(21) Appl. No.: **10/826,056**

(57) **ABSTRACT**

(22) Filed: **Apr. 16, 2004**

An imprinting apparatus and method of fabrication provide a mold having a pattern for imprinting. The apparatus includes a semiconductor substrate polished in a [110] direction. The semiconductor substrate has a (110) horizontal planar surface and vertical sidewalls of a wet chemical etched trench. The sidewalls are aligned with and therefore are (111) vertical lattice planes of the semiconductor substrate. The semiconductor substrate includes a plurality of vertical structures between the sidewalls, wherein the vertical structures may be nano-scale spaced apart. The method includes wet etching a trench with spaced apart (111) vertical sidewalls in an exposed portion of the (110) horizontal surface of the semiconductor substrate along (111) vertical lattice planes. A chemical etching solution is used that etches the (111) vertical lattice planes slower than the (110) horizontal lattice plane. The method further includes forming the imprinting mold.

(51) **Int. Cl.**
H01L 29/04 (2006.01)
H01L 31/036 (2006.01)

(52) **U.S. Cl.** **257/628; 257/622**

(58) **Field of Classification Search** 249/60, 249/69-71, 81; 205/70; 425/517, 112; 118/200, 118/211-212; 148/33.2; 438/700, 752-753; 257/618, 622, 627-628


See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

5,772,905 A 6/1998 Chou
6,294,450 B1 9/2001 Chen et al.
6,309,580 B1 10/2001 Chou

35 Claims, 9 Drawing Sheets






FIG. 1A




FIG. 1B




FIG. 1C




FIG. 2A




FIG. 2B





FIG. 2C

*FIG. 3A*




FIG. 3B




FIG. 3C




FIG. 3D




FIG. 3E




FIG. 4A




FIG. 4B




FIG. 4C




FIG. 4D




FIG. 4E

APPARATUS FOR IMPRINTING LITHOGRAPHY AND FABRICATION THEREOF

BACKGROUND

1. Technical Field

The invention relates to the fabrication of nano-scale and micro-scale structures. In particular, the invention relates to molds used in imprinting lithography.

2. Description of Related Art

A consistent trend in semiconductor technology since its inception is toward smaller and smaller device dimensions and higher and higher device densities. As a result, an area of semiconductor technology that recently has seen explosive growth and generated considerable interest is nanotechnology. Nanotechnology is concerned with the fabrication and application of so-called nano-scale structures, structures having dimensions that are often 50 to 100 times smaller than conventional semiconductor structures. Nano-imprinting lithography is a technique used to fabricate nano-scale structures.

Nano-imprinting lithography uses a mold to imprint nano-scale structures on a substrate. A mold typically contains a plurality of protruding and/or recessed regions having nano-scale dimensions. Such a mold is fabricated using electron beam (e-beam) lithography or patterning and dry etching, typically reactive ion etching (RIE) to create a nano-scale pattern in the mold. However, e-beam lithography is slow and therefore of limited use in high throughput or production situations. Moreover, e-beam lithography has limited resolution in the nano-scale range. For example, a mask prepared using micro or nano-patterning techniques (e.g., optical lithography or e-beam writing) has some residual roughness along mask pattern edges. RIE etching through the mask introduces surface roughness in the sidewalls of the patterns of the mold that at least mimic and may further exacerbate the edge roughness of the mask pattern. As such, the mask used in RIE etching defines the sidewall roughness of the nano-patterns of a mold and such roughness remains rough at the micro-scale even with extreme precision writing. Further, the RIE process causes crystal degradation to the mold material.

While holding much promise, the practical use of such fabricated molds has been somewhat limited. In particular, the surface roughness of the mold contributes to undesirable roughness of the imprint patterns of the mold. Further, crystal damage to the mold caused by RIE processing contributes to low mold reliability and limited mold useful life in manufacturing of nano-scale structures. Moreover, the fabrication of the molds is time consuming. As such, the conventional mold can be costly to use.

Accordingly, it would be desirable to fabricate a mold with higher reliability, higher nano-scale resolution, longer useful life and less surface roughness to the mold patterns using potentially low-cost, fabrication techniques at higher throughput. Such a fabricated mold would solve a long-standing need in the area of nanotechnology.

BRIEF SUMMARY

In some embodiments of the present invention, an imprinting apparatus is provided. The imprinting apparatus comprises a semiconductor wafer polished in a [110] direction. As such, the semiconductor wafer has a (110) horizontal planar surface. The semiconductor wafer further has vertical sidewalls of a wet chemical etched trench. The

trench vertical sidewalls are aligned with (111) vertical lattice planes of the semiconductor wafer. The semiconductor wafer comprises a plurality of vertical structures between the trench vertical sidewalls. The trench vertical sidewalls and the plurality of vertical structures are spaced apart from each other to form a mold that provides a pattern for imprinting.

In other embodiments of the present invention, a method of fabricating an imprinting apparatus is provided. The method of fabricating comprises wet etching a semiconductor wafer polished in a [110] direction. The semiconductor wafer has a (110) horizontal surface. A portion of the (110) horizontal surface is exposed. The exposed portion is aligned between (111) vertical semiconductor crystal lattice planes of the semiconductor wafer. The semiconductor wafer is wet etched with a chemical etching solution that etches the (111) vertical lattice planes slower than a (110) horizontal semiconductor lattice plane to form a trench having spaced apart (111) vertical sidewalls in the semiconductor wafer. The method of fabricating further comprises forming a mold with a pattern for imprinting. The vertical sidewalls have smooth surfaces relative to vertical sidewalls etched with a dry chemical etching process.

Certain embodiments of the present invention have other features in addition to and in lieu of the features described hereinabove. These and other features of some embodiments of the invention are detailed below with reference to the following drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

The various features of embodiments of the present invention may be more readily understood with reference to the following detailed description taken in conjunction with the accompanying drawings, where like reference numerals designate like structural elements, and in which:

FIG. 1A illustrates a perspective view of an embodiment of an imprinting apparatus according to an embodiment of the present invention.

FIG. 1B illustrates a perspective view of another embodiment of an imprinting apparatus according to an embodiment of the present invention.

FIG. 1C illustrates a perspective view of a semiconductor wafer or a semiconductor layer of semiconductor on insulator wafer polished in the [110] direction that illustrates (111) vertical crystal lattice planes in the semiconductor by dashed lines used for the apparatus and method according to embodiments of the present invention.

FIG. 2A illustrates a flow chart of an embodiment of a method of fabricating an imprinting mold according to an embodiment of the present invention.

FIG. 2B illustrates a perspective view of the semiconductor wafer or layer of FIG. 1C having a mask layer on the substrate surface according to an embodiment of the present invention.

FIG. 2C illustrates a perspective view of the semiconductor wafer or layer of FIG. 2B in which the mask layer is patterned to expose a portion of the underlying (110) horizontal surface of the semiconductor wafer according to an embodiment of the present invention.

FIG. 2D illustrates a perspective view of the semiconductor wafer or layer of FIG. 2C during wet chemical etching according to an embodiment of the present invention.

FIG. 2E illustrates a perspective view of the semiconductor wafer or layer of FIG. 2D at completion of wet chemical etching according to an embodiment of the present invention.

FIG. 3A illustrates a flow chart of another embodiment of a method of fabricating an imprinting mold according to an embodiment of the present invention.

FIG. 3B illustrates a side view of a semiconductor substrate polished in the [110] direction having an etched trench therein according to an embodiment of the present invention.

FIG. 3C illustrates a side view of the semiconductor substrate of FIG. 3B with alternating layers of different materials deposited in the trench of the semiconductor substrate according to an embodiment of the present invention.

FIG. 3D illustrates a side view of the semiconductor substrate of FIG. 3C with the alternating layers removed from a plane of the (110) horizontal surface according to an embodiment of the present invention.

FIG. 3E illustrates a side view of the semiconductor substrate of FIG. 3D after selective removal of one of the materials from vertical portions of respective alternating layers according to an embodiment of the present invention.

FIGS. 4A–4E illustrate side views of exemplary nano-structures being fabricated on a substrate using the apparatus of FIG. 1A or 1B according to an embodiment of the present invention.

DETAILED DESCRIPTION

FIG. 1A illustrates a perspective view of an embodiment of an imprinting apparatus 100 in accordance with an embodiment of the present invention. FIG. 1B illustrates a perspective view of another embodiment of an imprinting apparatus 100 in accordance with an embodiment of the present invention. The apparatus 100 is a nano-imprinting mold 100 having formed therein one or both of a nano-scale mold pattern and a micro-scale mold pattern that, when imprinted on a substrate surface, facilitates forming structures, such as nanowires or other circuit elements, on the substrate surface. The techniques for nano-imprinting with molds are known for example, from U.S. Pat. Nos. 5,772,905; 6,309,580; 6,294,450 and 6,407,443, all of which are incorporated herein by reference in their entirety. Such nano-imprinting techniques are applicable to micro-scale imprinting as well. Therefore while the following description uses the term or prefix ‘nano’ throughout, in accordance with the various embodiments of the present invention, usage of ‘nano’ is intended to include within its scope and to apply to ‘micro’ as well, without limitation, unless otherwise specified. A method of imprinting nano-structures with the apparatus 100 is described below.

Referring to FIG. 1A, the nano-imprinting apparatus 100 comprises a semiconductor wafer 102 that is polished in a [110] direction. In FIG. 1B, the nano-imprinting apparatus 100 comprises a semiconductor layer over an insulator layer both supported by a wafer polished in the [110] direction. In some embodiments, the apparatus 100 may comprise a silicon-on-insulator (SOI) substrate or wafer having a silicon layer 102 polished in the [110] direction, a silicon dioxide layer 116 and an underlying layer or remainder material 118 of the SOI wafer, typically of silicon or sapphire, for example. The silicon dioxide layer 116 is between the silicon layer 102 and the remainder material 118. FIG. 1C illustrates a perspective view of the semiconductor wafer 102 polished in the [110] direction according to an embodiment of the

present invention. FIG. 1C further exemplifies the silicon layer 102 of the SOI substrate or wafer polished in the [110] direction according to another embodiment of the present invention. For simplicity purposes only and not by way of limitation, the term ‘wafer’ will be used interchangeably herein to mean either a wafer 102 or a layer 102 of a semiconductor on insulator wafer including but not limited to, the silicon layer of the SOI wafer, unless otherwise specified.

For the purposes of the various embodiments of the present invention, the semiconductor wafer or layer (i.e., substrate) may be a single crystal semiconductor material having a diamond crystal structure or a compound semiconductor material having a zinc blende crystal structure, each polished in the [110] direction. As such, the term ‘semiconductor’, as used herein, is defined to mean one or both of a single crystal semiconductor material having a diamond crystal structure and a compound crystal semiconductor material having a zinc blende crystal structure. A single crystal semiconductor material includes, but is not limited to silicon and germanium (both Group IV). A zinc blende compound semiconductor material includes, but is not limited to, Group III–V compound semiconductors (e.g., GaAs and GaP) and Group II–VI compound semiconductors (e.g., CdTe and ZnS). See S. M. Sze, *Physics of Semiconductor Devices*, Second Edition, John Wiley & Sons, 1981, pp. 8–12 and Appendix F, incorporated herein by reference. Therefore while various embodiments of the present invention are described below using ‘silicon’ for the wafer material, such use of silicon is by way of example and not limitation. One skilled in the art may use any semiconductor material, as defined above, in the embodiments described herein, without undue experimentation, and still be within the scope of the various embodiments of the present invention.

By [110] direction, it is meant that a major horizontal planar surface 103 of the semiconductor wafer 102 is a (110) horizontal semiconductor crystal lattice plane. Moreover, the semiconductor wafer 102 has a plurality of (111) vertical semiconductor lattice planes 105 that intersect with the major horizontal surface 103. For the purposes of discussion herein, and not by way of limitation, the (110) horizontal crystal lattice plane is considered to be horizontally oriented with respect to a Cartesian coordinate system. The (110) horizontal surface 103 is a (110) horizontal plane. The (111) vertical lattice planes 105 are approximately perpendicular to and intersect with the (110) horizontal surface of the wafer. Therefore for the purposes of discussion herein, the (111) vertical planes are considered to be approximately vertically oriented relative to the (110) horizontal surface or plane of the semiconductor wafer. The use of brackets ‘[]’ and parenthesis ‘()’ herein pertains to a direction and a plane of a crystal lattice, respectively, when used herein to enclose such numbers as 110 and 111, and is intended to follow standard crystallographic nomenclature known in the art.

Referring back to FIGS. 1A and 1B, the nano-imprinting apparatus 100 further comprises opposing sidewalls 106 of a major trench 104 etched in the semiconductor wafer 102, hereinafter ‘silicon’ wafer 102 by way of example. The sidewalls 106 are internal to the trench 104. In particular, the sidewalls 106 are aligned with spaced-apart ones of the (111) vertical lattice planes 105. Therefore, the sidewalls 106 of the trench 104 are (111) vertical sidewalls 106. The sidewalls 106 have characteristically smooth surfaces due to the use of wet chemical etching to form the trench 104 rather than conventional dry etching techniques, such as reactive ion etching (RIE). In some embodiments, the silicon wafer

102 and in particular, the trench **104** has characteristically reduced crystal structure damage relative to when dry etching techniques (e.g., RIE) are used to form the trench **104**.

Wet chemical etching solutions that favor anisotropically etching in the vertical direction much more than the horizontal direction are particularly useful in achieving the mold **100** apparatus of the present invention. See for example, *High-Speed Semiconductor Devices*, Edited by S. M. Sze, A Wiley-Interscience Publication, John Wiley & Sons, Inc., 1990, at least Part I, Section 1.4, pp 33–51. Etching the silicon is described in more detail below with respect to a method of fabricating a nano-imprinting mold.

The nano-imprinting apparatus **100** further comprises a plurality of vertical structures **108** disposed in the trench **104** between the opposing sidewalls **106**. The vertical structures **108** are spaced from the opposing sidewalls **106** and further are spaced apart from each other in the trench **104**. A vertical structure **108** comprises opposing sides **107** and an end **109**. A side **107** of the vertical structure **108** faces one or both of a side **107** of an adjacent vertical structure **108** and a sidewall **106** of the trench **104**. In some embodiments, the vertical structures **108** are parallel to each other and to the trench sidewalls **106**. In some embodiments, the vertical structures **108** are either also perpendicular or alternatively perpendicular to the trench sidewalls **106** (not illustrated). The end **109** of the vertical structure **108** has a horizontal planar surface that is coplanar with the (110) planar surface **103** of the silicon wafer **102**.

In some embodiments, a spacing **112** between the plurality of vertical structures **108** may be considered a plurality of minor trenches **112** relative to the main or major trench **104**. In these embodiments, a minor trench **112** is no different from the major trench **104** except for relative trench width. For example, the sides **107** of the vertical structures **108** are (111) vertical sidewalls **107** of a minor trench **112** in these embodiments. These sidewalls **107** are (111) vertical lattice planes having essentially the same smoothness characteristic as that of the sidewalls **106**. However, in contrast to FIG. 1A, FIG. 1B further illustrates that the major trench **104** or each minor trench **112** of the plurality has a bottom that contacts the silicon dioxide layer **116** of the SOI wafer.

In other embodiments, the vertical structures **108** are formed separately from the major trench **104**. Moreover, the vertical structures **108** may be silicon or a different material than that of the silicon wafer **102**, such as silicon nitride, silicon dioxide, or germanium, for example.

The major trench **104** and the interspersed vertical structures **108** between the trench sidewalls **106** of the mold **100** have nano-scale spacing for subsequent nano-imprinting.

In some embodiments, the spacing and pitch of the trenches **112**, **104** or of the vertical structures **108** can range from about 10 nanometers (nm) to about 5 microns (μm) and in some embodiments, from about 5 nm to about 200 μm , as is further described below.

FIG. 2A illustrates a method **200** of fabricating an imprinting mold according to an embodiment of the present invention. FIGS. 2B–2E illustrate perspective views of a semiconductor wafer or layer polished in the [110] direction processed according to the method **200** of FIG. 2A. The method **200** of fabricating comprises wet etching **210** a semiconductor wafer polished in a [110] direction; and forming **220** a mold for nano-imprinting. The polished semiconductor wafer may be a stand-alone silicon wafer or a polished silicon layer of a silicon-on-insulator wafer or substrate, by way of example. Wet etching **210** comprises anisotropically etching along (111) vertical lattice planes with a chemical etching solution that etches much faster in

a vertical direction than the solution etches in a horizontal direction. The silicon wafer has etched **210** therein a trench with spaced apart (111) vertical sidewalls of silicon. Typically, the trench is relatively much longer than it is wide and further, is relatively much deeper than it is wide. However, the shape and dimensions of the trench depend on the nano-structure that is to be subsequently imprinted. Such shape and dimensions of the trench are controlled by an etch mask and the parameters of the wet etching process used, for example.

Silicon etching may be accomplished by exposing the silicon substrate to an etching solution, such as a potassium hydroxide (KOH) solution or an ethylene diamine pyrocatechol (EDP) solution, for example. Exposure to such etching solutions removes silicon material anisotropically to create the trench in the silicon substrate as defined by the etch mask. The target depth is achieved by adjusting the etching time along with solution concentration and temperature.

In an embodiment, the silicon is etched through an etch mask pattern with an etching solution that comprises about 44 weight percent (wt. %) potassium hydroxide with the balance being water (KOH—H₂O) at a temperature of about 120 degrees Centigrade ($^{\circ}\text{C}$.) that produces an etch rate of about 7 $\mu\text{m}/\text{min}$. The etch temperature may range from about room temperature or about 25 $^{\circ}\text{C}$. to about 150 $^{\circ}\text{C}$., depending on the embodiment. Moreover, the concentration of the KOH solution may range from about 5 wt. % to about 70 wt. %, depending on the embodiment.

In another embodiment, the silicon is etched through an etch mask pattern with an etching solution of EDP that comprises about 500 ml NH₂(CH₂)₂NH₂; about 88 g C₂H₄(OH)₂; about 234 ml H₂O at a temperature of about 110 $^{\circ}\text{C}$. In still another embodiment, the silicon is etched through an etch mask pattern with an etching solution of tetramethylammonium hydroxide (TMAH). TMAH allows for the use of different etch mask materials than those used with the KOH etching solution, as described further below.

For example, etching solutions such as KOH, EDP and TMAH attack or etch (111) planes in the silicon substrate as much as one hundred times more slowly than they etch other planes, e.g., the (110) planes. As such, relatively deep narrow trenches can be produced with depth-to-width aspect ratios of almost 100:1 when etching the (110) polished substrate through an etch mask.

According to the method **200**, the vertical sidewalls of the etched **210** trench have smooth surfaces relative to vertical sidewalls etched with the conventional dry chemical etching process. In some embodiments, the etched **210** silicon wafer further has reduced crystal structure damage relative to a silicon wafer etched with the conventional dry chemical etch process. The resultant silicon structure forms **220** a nano-scale mold for subsequent nano-imprinting that is more reliable and that may produce finer (i.e., less rough surfaces) nano-structures than conventional nano-imprinting molds.

The number of trenches that may be etched into a silicon wafer during the method **200** is dependent on the final nano-structure(s) to be subsequently imprinted and not considered a limitation herein. In some embodiments, a trench ultimately represents a nanowire (i.e., the trench is a negative of the nanowire) having a length, a width and a depth. Therefore, a mold may be formed **220** such that the trenches are spaced apart to achieve desired nanowire width, height and pitch in the final nano-structure. The final nano-structure achieved is limited by one or more of the capability of the

etching and/or lithographic technologies used and further, the atomic spacing of the (111) vertical lattice planes in the silicon, for example.

In some embodiments of wet etching **210**, the silicon wafer or SOI wafer with a silicon layer that is polished in the [110] direction is provided. Referring back to FIG. 1C, an exemplary silicon wafer or layer **202** polished in the [110] direction is illustrated. The term 'silicon wafer **202**' is used herein interchangeably with a silicon layer **202** of an SOI wafer that is polished in the [110] direction, unless stated otherwise. The silicon wafer **202** has a planar surface **203** aligned with a (110) horizontal silicon lattice plane. Silicon wafers and silicon-on-insulator (SOI) wafers polished in the [110] direction can be obtained from Isonics Corp., located in Golden, Colo. and Columbia, Md., having a website address of <http://www.isonics.com>. Another source for silicon wafers or silicon-on-insulator (SOI) wafers polished in the [110] direction is SOITEC USA Inc., Peabody, Mass., having a website address of <http://www.soitec.com>. Other semiconductor wafer materials may be obtained from one or both of these supplier as well.

In these embodiments, wet etching **210** further comprises masking the (110) horizontal surface **203** with an etch mask. A mask material is deposited and/or grown on the (110) horizontal surface of the silicon wafer **202**. FIG. 2B illustrates a perspective view of the semiconductor wafer **202** of FIG. 1C having a layer **211** of masking material covering the (110) horizontal surface **203**. Further illustrated in FIG. 2B are dashed lines **215** representing hypothetical alignment marks that align with underlying (111) vertical lattice planes **205** in the semiconductor wafer **202**.

In some embodiments, a thermal oxide layer **211** of silicon dioxide may be grown on the (110) horizontal surface **203** of the exemplary silicon wafer or layer **202**. A thermal oxide layer can be grown on the silicon surface according to known techniques using heat and, in some embodiments, the introduction of oxygen in a controlled atmosphere for the purposes of the method **200**. Alternatively or additionally, an oxide layer can be deposited on the silicon using plasma enhanced chemical vapor deposition (PECVD) at about 400° C., for example. A thermal oxide layer is more resistant to the KOH wet etching solution than the PECVD oxide layer, for example.

In other embodiments, the masking layer **211** is selected from an oxide material, a polymer material and a composite material that resists attack by the etchant solution used for anisotropically etching the semiconductor wafer **202**. For example, the oxide, polymer or composite masking layer **211** will resist one or more of KOH, EDP and TMAH attack during etching of the silicon wafer **202**. The oxide, polymer or composite masking layers **211** may be deposited or applied by spin coating onto the surface **203**, for example, using known techniques.

Once grown and/or deposited, the masking layer **211** is patterned to serve as the etch mask **211** for subsequent etching. As used herein, 'patterning' or 'patterned' refers to defining and producing a final pattern, or a final pattern defined and produced, in the masking layer, for example. As such, 'patterning' or 'patterned' is not limited to any process used to so define and produce such a final pattern. In particular, in some embodiments patterning the masking layer may comprises any technique including, but not limited to, conventional photolithography, imprint lithography and electron-beam lithography, along with an applied resist or similar masking material or masking process, or ion milling. With such patterning, a portion of the masking layer

211 is removed by one or both of reactive ion etching (RIE) and wet chemical etching, for example.

As used herein, 'etching' generally refers to any process by which material is removed either selectively or nonselectively. Thus, 'oxide etching' refers to any process that removes oxide of the oxide masking layer **211**. In some embodiments, dry chemical processing such as, but not limited to, using plasmas or ion beams, may be employed to etch the masking layer **211**. Moreover, patterning described hereinabove determines the locations of the mask etching.

For example, RIE may be employed to selectively etch the masking layer **211**. RIE is a specialized plasma dry chemical processing that is known to achieve anisotropic material removal. In another example, various plasmas can be used with an unbiased substrate to produce generally isotropic etching of the masking layer **211**. In yet another example, ion milling may be used to etch the masking layer **211**. Ion milling is a form of ion beam dry chemical processing that is inherently anisotropic. See for example, *High-Speed Semiconductor Devices*, cited supra, at pg. 49. In some embodiments, a photoresist mask is patterned on the oxide layer using conventional photolithography techniques that are known in the art. Then trifluoromethane (CHF₃) and Argon (Ar) gases are used in RIE to pattern the oxide layer through the photoresist mask, for example. Once the oxide layer is patterned with RIE, the photoresist mask is removed using known techniques.

Selective removal of portions of the masking layer **211** exposes selected portions of the underlying (110) horizontal surface **203** of the silicon substrate **202** while leaving other portions unexposed. The selected exposed and unexposed portions are defined by the aligned patterned edges of the etched mask layer **211**. The patterned mask layer **211** essentially forms an etch mask **211** for later processing of the silicon substrate **202**.

Mask edges **215** defined by patterning the masking layer establish locations on the (110) horizontal surface where the trench vertical sidewalls will be etched **210** in the silicon wafer. In particular, the edges of the etch mask **211** lie along, or are aligned with, the intersection of one or more (111) vertical lattice planes with the (110) horizontal surface of the silicon wafer. FIG. 2C illustrates a perspective view of the semiconductor wafer or layer **202** of FIG. 2B with a portion of the (110) horizontal surface **203** exposed after patterning the mask layer **211** to form the etch mask **211**.

In FIG. 2C, a portion **203a** of the (110) horizontal surface **203** is exposed. Edges **215** of the etch mask **211** are aligned with edges of the exposed (110) surface portion **203a** and coincide with intersecting (111) vertical lattice planes **205** of the silicon wafer **202**. The silicon wafer **202** is subsequently etched **210** between the edges **215** of the etch mask **211** from the exposed (110) surface portion **203a**, as described further below.

FIG. 2D illustrates a perspective view of the semiconductor wafer or layer of FIG. 2C during wet chemical etching according to an embodiment of the present invention. As illustrated in FIG. 2D, the exemplary silicon wafer **202** is being wet etched **210** anisotropically to form a trench **204** having parallel vertical sidewalls **206** along (111) vertical lattice planes **205**. Wet etching **210** is described in more detail above. FIG. 2E illustrates a perspective view of the semiconductor wafer or layer **202** of FIG. 2D at completion of wet chemical etching **210** according to an embodiment of the present invention.

The etch mask **211** is also removed from the (110) horizontal surface **203** of the silicon wafer **202** in FIG. 2E. The etch mask **211** is removed at the completion of wet

etching **210**, such as using hydrofluoric acid (HF) for a thermal oxide etch mask, for example, according to known techniques of oxide removal.

The etched trench **204** has a bottom **204a** that is approximately horizontal or laterally extending relative to the trench vertical sidewalls **206**. The shape of the trench bottom **204a** is illustrated generally as an approximate V-shape, but may be approximately U-shaped, some combination of the V and U shapes, or simply planar, without limitation herein. For example, in some embodiments that use an SOI wafer, the silicon layer is etched **210** according to the method **200**, until the etchant reaches the silicon dioxide layer. As such, the trench bottom is approximately planar or flat. As illustrated in FIG. 1B for example, the silicon dioxide layer **116** is between the silicon layer **102** and the remainder material layer **118** of the SOI wafer. The silicon dioxide layer **116** effectively provides the planar bottom of the etched trench.

FIG. 2E essentially illustrates an imprinting mold formed **220** by the method **200** of fabricating of the present invention. Only one trench **204** in the silicon wafer **202** of the mold is illustrated in FIG. 2E for simplicity, and not by way of limitation. The formed **220** mold may have a plurality of trenches similarly etched therein, as illustrated in FIGS. 1A and 1B, for example. In some embodiments, a mold with a plurality of trenches is formed **220** using the method **200** as described above, by patterning the masking layer **211** with a corresponding plurality of etch mask edge pairs **215** that is aligned with a plurality of spaced apart pairs of (111) vertical lattice planes **205**. A width of an etched trench **204** and the spacing between the etched trenches **204** essentially dictate a width and pitch of structures, respectively, subsequent formed by imprinting with the formed **220** mold. In some embodiments of the method **200**, the width of an etched trench **204** (or equivalently a space between adjacent (111) vertical sidewalls **206**) ranges from about 5 nm to about 100 μm . Moreover, in some embodiments of the method **200**, spacing of adjacent trenches **204** (i.e., pitch) may range from about 10 nm to about 200 μm . As mentioned above, the term or prefix 'nano' used herein is intended to include within its scope dimensions in one or both of a nanometer range and a micrometer range, without limitation.

In other embodiments, a mold with a plurality of trenches is formed by a method of fabricating an imprinting mold having a plurality of vertical structures. FIG. 3A illustrates a flow chart of an embodiment of a method **300** of fabricating an imprinting mold according to another embodiment of the present invention. FIGS. 3B–3E illustrate side views of a semiconductor substrate during fabrication according to the method of FIG. 3A. The semiconductor substrate may be a semiconductor wafer or a semiconductor layer of a semiconductor on insulator wafer, although the insulator layer is not illustrated in FIGS. 3B–3E. The method **300** of fabricating comprises wet etching **310** a semiconductor wafer polished in the [110] direction and is applicable to an exemplary silicon wafer or a silicon layer polished in the [110] direction of an SOI wafer, as essentially described above for wet etching **210** of the method **200** and includes FIGS. 2B–2E. FIG. 3B illustrates a side view of a semiconductor substrate **302** polished in the [110] direction having an etched trench **304** therein according to an embodiment of the present invention. While the bottom of the etched trench **304** of the semiconductor substrate illustrated in FIGS. 3B–3E has an approximate V-shape, in embodiments using the SOI wafer, the etched trench bottom in the polished silicon layer is relatively planar (not illustrated in FIGS. 3B–3E, see instead FIG. 1B). Moreover, the relatively planar trench bottom exposes the insulator layer, such as the silicon

dioxide layer that is between the silicon layer and the remainder material of the SOI wafer (not illustrated in FIGS. 3B–3E). The trench **304** comprises opposing vertical sidewalls **306** that are (111) vertical lattice planes **305** of the semiconductor substrate **302**, and a trench bottom **304a**. The opposing (111) vertical sidewalls **306** are smooth relative to trench sidewalls formed by a dry etching process. In some embodiments, the method **300** is essentially the method **200** that further comprises additional steps of forming **220** a mold.

As illustrated in FIG. 3A, the method **300** of fabricating further comprises depositing **320** alternating layers of a first material **322** and a second material **324** sequentially between the spaced apart (111) vertical sidewalls **306** of the trench **304**. The first material **322** is different from the semiconductor substrate and the second material. FIG. 3C illustrates a side view of the semiconductor substrate **302** of FIG. 3B with alternating layers **322**, **324** of different materials deposited in the trench **304** thereof. The alternating layers **322**, **324** are deposited to cover the sidewalls **306** and the relatively horizontally extending bottom **304a** of the trench **304**. The alternating layers **322**, **324** essentially fill the trench **304**.

In some embodiments, the first material **322** is selected from silicon, silicon dioxide, silicon nitride, germanium (Ge), for example, and the second material **324** is independently selected from silicon, silicon nitride, silicon dioxide, germanium, for example. A first layer of the first material is deposited adjacent to the substrate trench sidewall. The second material is deposited on the first material, followed by the first material on the second material, and so on. Deposition of these materials may use a chemical vapor deposition (CVD) process or another process, such as molecular beam epitaxy (MBE), for example. In some embodiments, a plasma enhanced chemical vapor deposition (PECVD) process is used. CVD, PECVD and MBE, and the corresponding gases for deposition are known in the art.

In some embodiments using the exemplary silicon wafer or layer, the alternating layers comprise silicon dioxide as the first material **322** and silicon nitride as the second material **324**. The silicon dioxide layer **322** and the silicon nitride layer **324** are deposited using CVD or PECVD. The materials are deposited using known techniques, such as using high temperature conditions (e.g., about 400° C.) with either an oxygen-containing gas or a nitrogen-containing gas, depending on the material being deposited. For embodiments using germanium as either the first material or the second material, a germane gas is used.

In some of these embodiments, the alternating layers **322**, **324** further cover the (110) horizontal surface **303** of the silicon wafer **302** at least adjacent to the trench **304**, as illustrated in FIG. 3C. Referring back to FIG. 3A, the method **300** of fabricating further comprises removing **330** the alternating layers **322**, **324** from a plane corresponding to the (110) horizontal surface **303** that extends cross the trench **304** in these embodiments. The alternating layers **322**, **324** are removed from the (110) horizontal surface **303** using one or both of chemical polishing and mechanical polishing. In some embodiments, a polishing slurry that only polishes mechanically is used, such that the materials are removed at approximately the same rate. Polishing slurries are known in the art. In other embodiments, both chemical polishing and mechanical polishing may be used with the caveat that chemical polishing may remove one material faster than the other material.

FIG. 3D illustrates a side view of the semiconductor substrate **302** of FIG. 3C with the alternating layers **322**, **324**

removed from a plane of the (110) horizontal surface **303**. The removal thereof forms an exposed planar surface aligned with the (110) horizontal surface **303** that extends across the trench **304**. As illustrated in FIG. 3D, vertically extending portions of each of the alternating layers **322**, **324** terminate or end at the exposed planar surface.

Referring back to FIG. 3A, the method **300** of fabricating further comprises selectively removing **340** a material from respective alternating layers. FIG. 3E illustrates a side view of the semiconductor substrate **302** of FIG. 3D after selective removal of one of the materials from vertical portions of respective alternating layers. In the embodiments using a silicon wafer and silicon dioxide as the first material **322** and silicon nitride as the second material **324**, the silicon dioxide material **322** is removed from between the silicon nitride layers **324** and from between the trench sidewalls and the silicon nitride layers **324**, as illustrated in FIG. 3E. The silicon dioxide **322** is removed **340** from the vertically extending portions thereof to a depth A illustrated in FIG. 3E. The trench **304** still comprises the alternating layers of silicon dioxide **322** and silicon nitride **324** between the trench bottom **304a** and the depth A. At the depth A, the trench **304** comprises a relatively flat or planar surface **312a** of silicon dioxide **322** between vertical structures or walls **308** of the silicon nitride **324**. The silicon dioxide **322** is selectively removed using hydrofluoric acid (HF), for example, or another selective etchant known in the art, that preferentially removes silicon dioxide instead of silicon, germanium and silicon nitride, for example, or removes the silicon dioxide faster than such other materials.

In another embodiment where silicon nitride is the first material **322** and either silicon, silicon dioxide or germanium is the second material **324**, the silicon nitride may be etched using RIE and tetrafluoromethane gas (CF₄) using known techniques. An etch mask that covers the second material **324** but leaves the silicon nitride exposed may be used during etching. Silicon nitride etches faster in CF₄ using RIE than does silicon dioxide, silicon and germanium, for example, such that relatively smooth walled trenches of depth A are formed.

A mold results that comprises a plurality of spaced apart vertical structures **308** extending parallel between the (111) vertical sidewalls **306** of the major trench **304**. A vertical structure **308** has wall surfaces **307** and an end **309**. Further, the removed first material **322** creates spaces **312** (or minor trenches **312** with relatively planar bottoms **312a**) between the vertical structures **308**. The space **312** between two adjacent vertical structures **308** is in the nano-scale range. Furthermore, the space **312** between a vertical structure **308** and an adjacent (111) vertical sidewall **306** is in the nano-scale range. However, the nano-scale spaces **312** achieved according to the method **300** of fabricating are much smaller than those achieved using the wet etching **210** of the method **200** to form **220** a mold with multiple trenches. This is because the alternating layers **322**, **324** are deposited at a thickness of as little as about 5 nm. The thickness of the deposited layers essentially dictates a width of the subsequent space **312** achieved. For some embodiments of the method **300**, the space **312** ranges from about 5 nm to about 500 nm.

FIGS. 1A and 1B illustrate a mold fabricated by either the method **200** or the method **300** of fabricating an imprinting mold, depending on the embodiment. As such, the mold ultimately produces nano-scale structures, such as nanowires, or other structural elements, having relatively smooth surfaces in one or both a nano-scale and a micro-scale range

of dimensions, as described above, during subsequent imprinting, depending on the embodiment of the present invention.

An example of nano-structure fabrication using the mold apparatus **100** of the present invention is described with reference to FIGS. 4A–4E. Nano-imprinting, as used herein, involves imprinting a negative image of a pattern of the mold **100** into a material relatively softer than the mold **100**. The softer material retains the imprinted pattern after the mold **100** is removed during further processing (see FIGS. 4A–4B). Typically, a layer of a thermoplastic polymer or UV-curable monomer or other suitable material is applied over a substrate comprising one or both of a semiconductor material and metal material. Thermoplastic polymers, such as polymethylmethacrylate (PMMA) and methylmethacrylate (MMA), or other suitable materials are described in U.S. Pat. No. 6,294,450 to Chen et al., which has been incorporated herein by reference. The imprinted pattern in the soft material layer is then transferred into the substrate as a positive image of the mold through lithography and etching, for example. The transferred pattern can be used for further processing in the formation of nano-scale structures, such as nanowires. There are many ways of transferring the pattern into the substrate. The method described herein is exemplary and provided with the understanding that the embodiments of the present invention are not so limited to the described method.

As illustrated in FIG. 4A, the substrate comprises a metal layer **406** deposited in a nano-scale thickness on a surface of a substrate **404**. The suitable soft material **402** is applied over the deposited metal **406**. The mold apparatus **100** is pressed into the softer material **402** and removed, leaving the mold pattern in the soft material, as illustrated in FIG. 4B. The mold pattern has thick portions **402a** and relatively thinner portions **402b**. The thinner portions **402b** of the soft material **402** are removed, such as by etching with an etchant that removes the soft material **402** in the thin portions **402b** but that does not etch the metal layer **406**. As illustrated in FIG. 4C, portions of the metal layer are exposed after the removal of the thinner portions **402b** of the soft material **402**. The exposed portions of the metal layer **406** are then removed using known techniques, leaving only those portions **406a** of the metal layer **406** covered by the thicker portions **402a** of the soft material **402**, as illustrated in FIG. 4D. These portions directly correspond to the trenches **104**, **112** in the mold **100**. FIG. 4E illustrates the substrate **404** with the remaining soft material **402a** removed from the remaining metal portions **406a**. The remaining metal portions **406a** in FIG. 4E represent nano-structures **406a**. Depending on the mold pattern and the embodiment, the nano-structures may be nanowires that run parallel to each other, for example, on the surface of the substrate, or that form a circuit pattern. Further nano-scale devices may be fabricated using these nanowires and the imprinting mold **100**. Likewise, micro-scale circuit elements may be imprinted on a substrate using the imprinting mold **100** described herein. For example, the imprinting mold **100** may be used to fabricate micro-scale memory circuit elements on a substrate.

In some embodiments, the subsequent nano-structures have much smoother sidewall surfaces than when e-beam patterning and RIE is used to make the corresponding nano-imprinting mold. The mold's trench sidewalls are atomic flat (i.e., relatively smooth even when measured at the atomic level) when etched along the (111) vertical planes with the wet chemical etchant, according to embodiments of

the present invention. Therefore, the corresponding nano-structure sidewalls are atomic flat.

Moreover, in embodiments of the mold made according to the method 300, the first and second materials grown on the wet etched (111) vertical sidewalls of the major trench will be only slightly rougher than the atomic flat (111) vertical sidewall surface. For example, the root-mean-square (RMS) roughness of the (111) vertical sidewall may be about 0.1 nm to about 0.5 nm and an oxide or nitride layer grown on the (111) sidewall has a roughness of about 0.1 nm to about 3 mm. As such, in some embodiments, the nano-structures formed using a mold fabricated according to the method 300 have much smoother sidewall surfaces than if those nano-structures were formed using a mold fabricated conventionally with e-beam lithography and RIE.

The apparatus 100 and method 200, 300 of fabricating according to embodiments of the present invention further provide a relatively easy mold release characteristic because the (111) vertical sidewalls of the mold are smooth when compared to a mold created using conventional e-beam lithography and RIE processes. Moreover, the apparatus 100 and method 200, 300 of fabricating provide a more durable mold than that produced using the conventional RIE processes. The mold is more durable because crystal damage to the silicon caused by RIE is essentially eliminated during the fabrication process according to embodiments of the present invention. Furthermore, the method 200, 300 of fabricating is more amenable to industrial production of molds, due to a higher volume throughput capability, since the method 200, 300 essentially eliminates using e-beam lithography.

Thus, there have been described embodiments of an imprinting apparatus and embodiments of a method of fabricating an imprinting mold. It should be understood that the above-described embodiments are merely illustrative of some of the many specific embodiments that represent the principles of the present invention. Clearly, those skilled in the art can readily devise numerous other arrangements without departing from the scope of the present invention as defined by the following claims.

For example, it should be clear to one skilled in this art that the application of the teachings hereinabove to silicon, which has a diamond crystal structure, may be extended to other materials having a zinc blende crystal structure, as mentioned above. Non-limitive examples include germanium and tin (Group IV elements), Group III-V compound semiconductors, such as arsenides (As), phosphides (P) and antimonides (Sb) of any of aluminum (Al), gallium (Ga), and indium (In) (e.g., GaAs, AlP, InSb), and Group II-VI compound semiconductors, such as CdS, CdSe, CdTe and ZnS). Those skilled in the art would readily know which reagents may be used to perform the preferential etching of these materials, as described above for silicon, without undue experimentation.

By way of example, GaAs (a Group III-V zinc blende compound semiconductor) may be etched along (111) planes using a solution of $H_2SO_4:H_2O_2:H_2O$ in a ratio of about 1:1:100 (see for example, S. Hirose et al, *Appl. Phys. Letts.* 74 (1999) 964-966, incorporated herein by reference). Moreover, it is within the scope of the various embodiments described herein to use a combination of dry and wet etching processes for some semiconductor wafers, such as for a Group III-V compound semiconductor. For example, using vertical dry etching (e.g., RIE) followed by wet etching to smooth the dry-etched surface may be used for generating vertical (111) planes.

Moreover, references that provide materials and processes useful for processing other semiconductor materials in more

detail include, but are not limited to, *Modern GaAs Processing Methods* by Ralph E. Williams, Artech House, (July 1990); *InP-Based Materials and Devices: Physics and Technology* by Osamu Wada (Editor), Hideki Hasegawa (Editor), Wiley-Interscience, (April 1999), pp. 295-309; *InP and Related Compounds: Materials, Applications and Devices* (Optoelectronic Properties of Semiconductors and Superlattices), M. O. Manasreh (Editor), Taylor & Francis, (Aug. 1, 2000); and *Physical Properties of III-V Semiconductor Compounds: InP, InAs, GaAs, GaP, InGaAs, and InGaAsP* by Sadao Adachi, Wiley-Interscience, (Sep. 1, 1992), each incorporated by reference herein. These and other references, such as *High-Speed Semiconductor Devices*, Edited by S. M. Sze, A Wiley-Interscience Publication, John Wiley & Sons, Inc., 1990, and S. M. Sze, *Physics of Semiconductor Devices*, Second Edition, John Wiley & Sons, 1981, also incorporated by reference herein, are readily available to those skilled in the art, such that other semiconductor materials, as defined above, may be used in the embodiments herein without undue experimentation.

What is claimed is:

1. An imprinting apparatus comprising:

a semiconductor substrate polished in a [110] direction, the semiconductor substrate having a (110) horizontal planar surface and vertical sidewalls of a wet chemical etched trench, the trench vertical sidewalls being aligned with (111) vertical lattice planes of the semiconductor substrate; and

a plurality of vertical structures disposed in the trench between the trench vertical sidewalls, a material of the vertical structures being different from a material of the semiconductor substrate,

wherein the plurality of vertical structures are spaced apart from each other and from the trench vertical sidewalls to form a mold that provides a pattern for imprinting.

2. The imprinting apparatus of claim 1, wherein the semiconductor substrate is wet chemical etched along the (111) vertical lattice planes using an etching solution that etches the (111) vertical lattice plane much slower than a (110) horizontal lattice plane to form the trench.

3. The imprinting apparatus of claim 1, wherein the semiconductor substrate is silicon, the etching solution being selected from potassium hydroxide, ethylene diamine pyrocatechol and tetramethylammonium hydroxide.

4. The imprinting apparatus of claim 1, wherein the semiconductor substrate is a material selected from one of a Group IV element, Group III-V elements, and Group II-VI elements, the semiconductor substrate being wet chemical etched along the (111) vertical lattice planes.

5. The imprinting apparatus of claim 1, wherein the semiconductor substrate is wet chemical etched along the (111) vertical lattice planes such that the trench sidewalls have smooth surfaces relative to trench sidewalls that are dry chemical etched.

6. The imprinting apparatus of claim 1, wherein the semiconductor substrate is wet chemical etched along the (111) vertical lattice planes such that the trench sidewalls have reduced crystal structure damage relative to trench sidewalls that are dry chemical etched.

7. The imprinting apparatus of claim 1, wherein the semiconductor substrate is a silicon layer of a silicon-on-insulator wafer polished in the [110] direction.

8. The imprinting apparatus of claim 1, further comprising:

nano-scale thick layers of a first material alternating with a layer of the vertical structure material in the trench,

15

the first material being different from the semiconductor substrate material and the vertical structure material, one of the first material layers being adjacent to the semiconductor substrate.

9. The imprinting apparatus of claim 8, wherein the semiconductor substrate is silicon, the first material being selected from silicon dioxide, silicon nitride and germanium, the vertical structure material being selected from silicon dioxide, silicon nitride and germanium.

10. The imprinting apparatus of claim 8, wherein the first material layers have a thickness that defines spaces between the vertical structures of the plurality and further defines spaces between each trench sidewall and a vertical structure of the plurality that is adjacent to the trench sidewall.

11. The imprinting apparatus of claim 8, wherein the vertical structure material layer has vertically extending portions that are the vertical structures of the plurality.

12. The imprinting apparatus of claim 8, wherein the first material layers and the vertical structure material layer define an internal depth of the imprinting apparatus.

13. The imprinting apparatus of claim 1, wherein the mold pattern has a vertical structure spacing in one or both of a nanometer range and a micrometer range.

14. A nano-imprinting apparatus comprising:

a semiconductor substrate having a horizontal (110) planar surface and (111) vertical lattice planes intersecting the (110) planar surface;

sidewalls of a trench etched in the semiconductor substrate along spaced apart (111) vertical lattice planes using wet chemical etching, such that the trench sidewalls are (111) vertical planes; and

a plurality of vertical structures disposed in the trench, the vertical structures being nano-scale spaced apart and spaced from the trench sidewalls, a vertical structure of the plurality having opposing sides and an end, a side of the vertical structure facing one of a side of an adjacent vertical structure and a trench sidewall, the end having a horizontal surface coplanar with the (110) planar surface of the semiconductor substrate, a material of the plurality of vertical structures being different from a material of the semiconductor substrate,

wherein the plurality of vertical structures between the trench sidewalls provides a nano-scale pattern for nano-imprinting.

15. The nano-imprinting apparatus of claim 14, wherein the trench is wet chemical etched along the (111) vertical lattice planes using an etching solution that etches the (111) vertical lattice plane much slower than the (110) planar surface.

16. The nano-imprinting apparatus of claim 15, wherein the semiconductor substrate is silicon, the etching solution being selected from potassium hydroxide, ethylene diamine pyrocatechol and tetramethylammonium hydroxide.

17. The nano-imprinting apparatus of claim 14, wherein the semiconductor substrate is a material selected from one of an element from Group IV, elements from Group III-V, and elements from Group II-VI.

18. The nano-imprinting apparatus of claim 14, wherein the sidewalls of the trench have one or both of smooth sidewalls and reduced crystal structure damage relative to trench sidewalls that are dry chemical etched.

19. The nano-imprinting apparatus of claim 14, wherein the semiconductor substrate is a silicon layer of a silicon-on-insulator wafer polished in a [110] direction.

16

20. The nano-imprinting apparatus of claim 14, wherein the vertical structures comprise a material selected from silicon, silicon dioxide, silicon nitride and germanium deposited in the trench by a chemical vapor deposition.

21. The nano-imprinting apparatus of claim 14, further comprising:

deposited nano-scale thick layers of a first material alternating with deposited nano-scale thick layers of the vertical structure material in the trench, the first material being different from the material of the semiconductor substrate and the vertical structure material, one of the first material layers being adjacent to the semiconductor substrate.

22. The nano-imprinting apparatus of claim 21, wherein the semiconductor substrate is silicon, the first material being selected from silicon dioxide, silicon nitride and germanium, the vertical structure material being selected from silicon dioxide, silicon nitride and germanium.

23. The imprinting apparatus of claim 21, wherein the nano-scale thickness of the first material layers define spaces between the vertical structures of the plurality and define spaces between each trench sidewall and a vertical structure of the plurality adjacent to the trench sidewall.

24. The nano-imprinting apparatus of claim 14, wherein the nano-scale pattern has one or both of a vertical structure spacing that ranges from about 5 nm to about 100 μm and a vertical structure pitch that ranges from about 10 nm to about 200 μm .

25. The imprinting apparatus of claim 14, further comprising:

layers of a first material alternating with layers of the vertical structure material in the trench, the first material layers and the vertical structure material layers in the trench defining an internal depth of the imprinting apparatus.

26. The imprinting apparatus of claim 25, wherein the layers of vertical structure material have vertically extending portions that are the plurality of vertical structures.

27. The imprinting apparatus of claim 25, wherein the first material layers have a thickness that defines spaces between the vertical structures of the plurality and defines spaces between each trench sidewall and a vertical structure of the plurality adjacent to the trench sidewall.

28. An imprinting apparatus comprising:

a substrate that is a semiconductor polished in a [110] direction, the substrate having a trench with sidewalls that are vertical, the sidewalls being aligned with (111) vertical lattice planes of the substrate; and

a plurality of vertical structures disposed in the trench between the sidewalls, a material of the vertical structures being distinct from a material of the substrate, wherein the vertical structures are spaced apart from each other and from the sidewalls of the trench to form a mold that provides a pattern for imprinting.

29. The imprinting apparatus of claim 28, further comprising:

a first material disposed in the trench that is different from the vertical structure material and the substrate material, the first material being between some of the vertical structures of the plurality to define spaces between the vertical structures, the first material further being between each sidewall of the trench and an adjacent vertical structure of the plurality to define spaces between the sidewalls and the adjacent vertical structures, the first material defining an internal depth of the imprinting apparatus.

17

30. The imprinting apparatus of claim 28, further comprising:

alternating layers of a first material and the vertical structure material in the trench, the first material being different from the vertical structure material and the substrate material, one of the first material layers being adjacent to the substrate, the alternating layers defining an internal depth of the imprinting apparatus.

31. The imprinting apparatus of claim 30, wherein the layers of the vertical structure material have vertical portions corresponding to the vertical structures of the plurality, a thickness of the first material layers defining spaces between the vertical structures of the plurality and further defining spaces between each sidewall and a vertical structure of the plurality that is adjacent to the sidewall.

32. An imprinting apparatus comprising:

a semiconductor substrate polished in a [110] direction, the semiconductor substrate having a trench with sidewalls that are vertical, the sidewalls being aligned with (111) vertical lattice planes of the semiconductor substrate;

a plurality of vertical structures disposed in the trench between the sidewalls, and

18

alternating layers of a first material and a second material in the trench, the second material layers having portions that extend vertically, the vertically extending portions being the plurality of vertical structures, the first material being different from the second material, wherein the vertical structures are spaced apart from each other and from the sidewalls of the trench to form a mold that provides a pattern for imprinting.

33. The imprinting apparatus of claim 32, wherein one layer of the first material is adjacent to the semiconductor substrate in the trench, a thickness of the first material layers defines spaces between vertical structures of the plurality and further defines spaces between the sidewall of the trench and a vertical structure of the plurality that is adjacent to the sidewall.

34. The imprinting apparatus of claim 32, wherein each of the first material, the second material and a material of the semiconductor substrate are different from one another.

35. The imprinting apparatus of claim 32, wherein the alternating layers define an internal depth of the imprinting apparatus.

* * * * *